

[illegible][illegible][illegible][illegible][illegible][illegible][illegible]

considered that an information network using optical fibers, coaxial cables or the like is established inside an intelligent building or a FA factory so that information can be transmitted/received rapidly and accurately. However, there is a problem, in this method, that construction of such a network costs a lot of money. Therefore, there has been proposed another method in which the whole building is shielded from the outside environment and information exchange inside the building is carried out by wireless communication. In order to effect this method, it has conventionally been attempted that metal plates or metal foils of iron, copper, aluminum or the like as electromagnetic wave shielding materials are laminated to building materials such as board materials or a wall material which shields electromagnetic wave is employed.

Further, at opening/closing portions such as doors and windows, a gasket for shielding electromagnetic wave is generally provided, so that the undesirable electromagnetic wave radiated from outside of the environment, as well as the electromagnetic wave which leaks from inside of the environment, can be shielded.

Examples of such a gasket include a gasket produced by the steps of: slicing an elastic foam block such as polyurethane sponge by a predetermined thickness by a slicer; cutting each slice to pieces having a predetermined width, thereby to obtain short, strap-like structures each having a rectangular section; optionally connecting one

in the thickness direction is poor. In addition, this conventional method ends up with a high production cost because it requires a number of production steps, such as compressing the slices under an increased pressure.

A gasket can be produced by what is called "the continuous foaming method" which includes the steps of: inserting a conductive woven cloth into a mold so that a hollow portion is created therein; and filling the hollow portion with a foaming raw material, with allowing the foaming raw material to foam, thereby producing a gasket. However, when a gasket is produced in such a manner, setting of the processing conditions (including selection of the raw material for effecting foaming, the charging and foaming method, the temperature condition) is difficult and thus high-standard control technique is required, resulting in a high facility cost, although the production efficiency thereof is relatively high. Further, in the gasket of such a type, the dimension accuracy may be relatively poor because foaming tends to proceed to some extent even after the foamed product is pulled out of the mold.

In recent years, as the electric appliances are becoming thinner, a gasket material having thickness of 100-1000 μm or so is now increasingly in demand. This trend has made the aforementioned problem even more obvious.

The thickness of a conductive woven cloth produced by providing a woven cloth with conductivity is generally 60-200 μm or so, and the thickness of a conductive unwoven

cloth produced by providing a unwoven cloth with conductivity is generally 60-500 μm or so. Such a conductive woven/unwoven cloth, which is made of only the conductive material, may be used as a thin gaslekt material. However, as the conductive woven/unwoven cloth made of only the conductive material exhibits poor cushioning property, the conductive woven/unwoven cloth of such a type is not suitable as a gasket material.

Further, the conductive material produced by forming a metal layer on the surface of a porous skeleton such as a strap-shaped, urethane sponge-like elastic foam structure (the polyurethane porous structure, in particular) has defects such as poor deterioration resistance property, although the conductive material of such a type shows relatively excellent electromagnetic wave shielding property. Yet further, the conductive material of this type hardly obtains sufficient flame resistance, and if a relatively large amount of flame retardant agent is provided thereto, the deterioration may proceed worse.

In JP-A 2001-3264, there is disclosed a knitted-woven fabric having a three dimensional structure with continuous holes, in which structure metal is attached to at least a portion of the structure thread and at least a portion of the structure thread is a conductive fiber. The publication states that the structure as described above allows a more degree of freedom in designing, enables obtaining three-dimensional structures of various sizes,

[illegible][illegible]

	1970	1971	1972	1973	1974	1975	1976	1977	1978	1979	1980	1981	1982	1983	1984	1985	1986	1987	1988	1989	1990	1991	1992	1993	1994	1995	1996	1997	1998	1999	2000	2001	2002	2003	2004	2005	2006	2007	2008	2009	2010	2011	2012	2013	2014	2015	2016	2017	2018	2019	2020	2021	2022	2023	2024	2025	2026	2027	2028	2029	2030	2031	2032	2033	2034	2035	2036	2037	2038	2039	2040	2041	2042	2043	2044	2045	2046	2047	2048	2049	2050	2051	2052	2053	2054	2055	2056	2057	2058	2059	2060	2061	2062	2063	2064	2065	2066	2067	2068	2069	2070	2071	2072	2073	2074	2075	2076	2077	2078	2079	2080	2081	2082	2083	2084	2085	2086	2087	2088	2089	2090	2091	2092	2093	2094	2095	2096	2097	2098	2099	2100	2101	2102	2103	2104	2105	2106	2107	2108	2109	2110	2111	2112	2113	2114	2115	2116	2117	2118	2119	2120	2121	2122	2123	2124	2125	2126	2127	2128	2129	2130	2131	2132	2133	2134	2135	2136	2137	2138	2139	2140	2141	2142	2143	2144	2145	2146	2147	2148	2149	2150	2151	2152	2153	2154	2155	2156	2157	2158	2159	2160	2161	2162	2163	2164	2165	2166	2167	2168	2169	2170	2171	2172	2173	2174	2175	2176	2177	2178	2179	2180	2181	2182	2183	2184	2185	2186	2187	2188	2189	2190	2191	2192	2193	2194	2195	2196	2197	2198	2199	2200	2201	2202	2203	2204	2205	2206	2207	2208	2209	2210	2211	2212	2213	2214	2215	2216	2217	2218	2219	2220	2221	2222	2223	2224	2225	2226	2227	2228	2229	2230	2231	2232	2233	2234	2235	2236	2237	2238	2239	2240	2241	2242	2243	2244	2245	2246	2247	2248	2249	2250	2251	2252	2253	2254	2255	2256	2257	2258	2259	2260	2261	2262	2263	2264	2265	2266	2267	2268	2269	2270	2271	2272	2273	2274	2275	2276	2277	2278	2279	2280	2281	2282	2283	2284	2285	2286	2287	2288	2289	2290	2291	2292	2293	2294	2295	2296	2297	2298	2299	2300	2301	2302	2303	2304	2305	2306	2307	2308	2309	2310	2311	2312	2313	2314	2315	2316	2317	2318	2319	2320	2321	2322	2323	2324	2325	2326	2327	2328	2329	2330	2331	2332	2333	2334	2335	2336	2337	2338	2339	2340	2341	2342	2343	2344	2345	2346	2347	2348	2349	2350	2351	2352	2353	2354	2355	2356	2357	2358	2359	2360	2361	2362	2363	2364	2365	2366	2367	2368	2369	2370	2371	2372	2373	2374	2375	2376	2377	2378	2379	2380	2381	2382	2383	2384	2385	2386	2387	2388	2389	2390	2391	2392	2393	2394	2395	2396	2397	2398	2399	2400	2401	2402	2403	2404	2405	2406	2407	2408	2409	2410	2411	2412	2413	2414	2415	2416	2417	2418	2419	2420	2421	2422	2
--	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	------	---

[illegible][illegible]

In the third aspect of the present invention, the aforementioned electromagnetic wave shielding material is characterized in that the heat-fusing thread is used by the amount of 30 to 90 mass % of the thread as one constituent of the three dimensionally knitted base material.

In the fourth aspect of the present invention, the aforementioned electromagnetic wave shielding material is characterized in that the heat-fusing thread is a composite thread having a core-sheath structure in which the core of the thread is made of polyester of one type and the sheath portion of the thread is made of polyester of another type whose melting point is lower than that of the polyester of the one type, and the weight ratio of the core with respect to the sheath is in the range of 1:2 to 9:1.

In the fifth aspect of the present invention, the aforementioned electromagnetic wave shielding material is characterized in that the connection thread of the three dimensionally knitted base material is provided so that, at a sectional portion of the three dimensionally knitted base material, the direction in which the connection thread is arranged avoids intersecting the sectional plane.

In the sixth aspect of the present invention, the aforementioned electromagnetic wave shielding material is characterized in that the three dimensionally knitted base material has a double raschel structure.

In the seventh aspect of the present invention, the aforementioned electromagnetic wave shielding material is

characterized in that a conductive metal layer of the electromagnetic wave shielding material is coated with a synthetic resin.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a schematic sectional view of one example of a three dimensionally knitted base material of the present invention;

Fig. 2 is a schematic perspective view of one example of a three dimensionally knitted base material of the present invention;

Fig. 3 is a structural view of one example of a three dimensionally knitted base material, which includes a portion in which connection thread is not present, of the present invention;

Fig. 4 is a structural view of the three dimensionally knitted base material of example 1; and

Fig. 5 is a structural view of the three dimensionally knitted base material of example 3. In Figs. 3-5, A denotes the number of battens and B denotes structure.

DETAILED DESCRIPTION OF THE INVENTION

In the present invention, the type of the base material is not particularly restricted as long as the base material can have a three dimensional structure. However, it is preferable to employ a three dimensionally (woven-)knitted base material, which includes, as main constituent members,

0596058-062901

an upper ground structure, a lower ground structure and a connection thread for connecting the upper ground structure and the lower ground structure and is produced by knitting by a double row needle bed type weaving-knitting machine. Among the three dimensionally knitted base material, that having the double raschel knitting structure is particularly preferable. The base material having such a structure exhibits excellent recovering property from compression, as well as excellent deterioration resistance property, and thus can be preferably used as an electromagnetic wave shielding material for a gasket or the like.

Examples of the fiber material which constitutes the fibrous structure knitted base material include the conventionally known base materials such as synthetic fiber and natural fiber. Among these examples, polyester fiber such as polyethyleneterephthalate, which has excellent resilience recovering property and deterioration resistance property, is preferable.

Further, it is preferable that a heat-fusing thread is used as the fiber material which constitutes the fibrous structure knitted base material. The type of the heat-fusing thread to be used is not particularly restricted, and examples thereof include a heat-fusing thread which is as a whole constituted of a low-melting point thread, a heat-fusing thread which is produced by side-by-side type composite spinning of a high-melting point thread and a

low-melting point thread and the like. Among these examples, it is preferable to use a polyester-based heat-fusing thread of the core-sheath composite type in which a high-melting point polyester (what is called "regular polyester") is used for the core portion and a low-melting point polyester is used for the sheath portion. It is preferable that the melting point of the low-melting point thread is in the range of 100 to 190 °C. When the melting point of the low-melting point thread is lower than 100 °C, the thread may melt during the use thereof as a shield material. On the other hand, when the melting point of the low-melting point thread is higher than 190 °C, the thread may not be fused in an appropriate manner.

It is preferable that the weight ratio of the core with respect to the sheath is in the range of 1:2 to 9:1. When the ratio of the core with respect to the sheath is smaller than the aforementioned lower limit (1:2), there may arise a problem in the strength of the thread. On the other hand, when the ratio of the sheath with respect to the core is smaller than the aforementioned lower limit (9:1), the sufficient adhesion effect of the thread may not be obtained.

The heat-fusing thread may be used at any of the upper ground structure, the lower ground structure and the connection thread of the three dimensionally knitted base material. Use of the heat-fusing thread at the portions which constitute the upper ground structure and the lower

ground structure is particularly preferable, because the low-melting point thread is fused at the time of processing and is attached with each other, whereby the amount of cutting debris generated at the time of cutting can be reduced.

The fiber material may be produced by knitting a high-melting point thread (regular thread) and a heat-fusing thread in an alternate or mixed manner.

Examples of the connection thread used in the three dimensionally knitted base material of the present invention include: the connection thread having a normally intersecting connection thread which connects the upper ground structure with the lower ground structure in a manner that the connection thread (substantially) normally intersects the upper ground structure and the lower ground structure; the connection thread having a diagonally intersecting connection thread which connects the upper ground structure with the lower ground structure in a manner that the connection thread diagonally intersects the upper ground structure and the lower ground structure; the connection thread having a truss structure which includes both the normally intersecting connection thread and the diagonally intersecting connection thread in a combined manner. In terms of effectively achieving the resilient elasticity of the base material and reducing the compressive residual strain, the connection thread having the diagonally intersecting connection thread is

preferable.

Further, in order to obtain sufficient resilient elasticity, reduce the compression residual strain and decrease the amount of cutting debris generated at the time of cutting the electromagnetic wave shielding material, it is preferable that the monofilament-based connection thread is used.

Yet further, it is preferable that the three dimensionally knitted base material is structured such that the base material has portions at which the direction of cutting (i.e., the cutting blade) can avoid intersecting the connection thread. When the three dimensionally knitted base material has such a structure, by cutting the three dimensionally knitted base material at these portions, the generation of debris at the time of cutting can be further suppressed.

Fig. 2 is a schematically illustrated perspective view which shows one example of the arrangement of the connection thread in the three dimensionally knitted base material of the present invention. The upper ground structure is connected with the lower ground structure by arranging, on the knitting device, the portions having the connection thread and the portions not having the connection thread, with a predetermined distance therebetween, in the well direction and/or the course direction of the knitted base material, as shown in Fig. 2. By cutting the three dimensionally knitted base material at

the portions not having the connection thread at the time of cutting, the amount of cutting debris generated at the time of cutting can be suppressed.

The portion not having the connection thread may be located in both the well direction and the course direction, or may be located only in one of these directions of the three dimensionally knitted base material. In short, the portion not having the connection thread may be provided in any suitable manner, according to the condition in which the three dimensionally knitted base material is actually used.

Further, at the time of connecting the connection thread to the upper ground structure and the lower ground structure by arranging the connection thread in the ground structures in the well direction and/or the course direction with a predetermined distance therebetween, as shown in Fig. 2, by knitting the connection thread into the same ground structure again (without knitting the connection thread into the opposite ground structure) at a predetermined interval, the portions having the connection thread and the portions not having the connection thread can be alternately produced. The interval between the portions having the connection thread and the portions not having the connection thread can be set at any suitable distance. In addition, the thickness of the three dimensionally knitted structure, the density of the thread, and the type of the thread which to be used can be changed

according to the conditions in which the three dimensionally knitted base material is actually used. Accordingly, the three dimensionally knitted structure of the present invention can be flexibly modified to different sizes. The structure shown in Fig. 3 is simply one example, and needless to say, the present invention is not restricted to this particular example.

The ground structures are preferably constructed so as to be hardly extended. If the ground structures have good extensibility, the space between the thread clusters tends to widen due to deformation of the ground structures, whereby the electromagnetic wave shielding property may deteriorate and/or the metal layer may more easily peel off. Therefore, the three dimensionally knitted base material having the structure in which no opening portion is provided at either the upper ground structure or the lower ground structure is preferably employed. Examples of the preferable structure of such a type include the combination of a chain structure and a code structure, and the like.

In addition, it is preferable that the density of the thread which constitutes the ground structure is relatively high.

As a result of the structures described above, the electromagnetic wave shielding material of the present invention exhibits excellent electromagnetic wave shielding property.

antimony trioxide; and the phosphorus-based flame retardant. These examples of the flame retardant may be used solely or in a combined manner. The combination of the bromine-based flame retardant and the antimony-based flame retardant, in particular, exhibits an excellent effect in use. Examples of the method of providing the flame retardant include padding, knife coating, and gravure coating of the mixture of the flame retardant and a solvent-based or water-based synthetic resin. As the fire retardancy of the product is improved as a result of adding the flame retardant, the product can be used in the fields where excellent fire retardancy is required, such as electric appliances for domestic use.

As described above, the electromagnetic wave shielding material of the present invention employs the three dimensionally knitted base material such as the double raschel knitting structure. Accordingly, by setting the types of the thread to be used, the denier of the thread, the number of filament count, the knitting structure and/or the knitting density in an appropriate manner, the properties of the electromagnetic wave shielding material (such as flexibility) can be controlled. Further, the base material of the double raschel knitting structure can be shaped so as to have any desired shape. For example, the base material of such a type can be shaped so as to have a toroidal shape by removing the center portion thereof by using die-cutting. By designing a three dimensionally

knitted structure having the required thickness, the electromagnetic wave shielding property of the product is further improved.

Yet further, the electromagnetic wave shielding material of the present invention can be used, not only for a gasket, but also for a taping material (a grounding material).

Examples

The present invention will be specifically demonstrated by the following examples. The method of measurement used in the examples are as follows.

1. Thickness

Measurement was made according to JIS L-1098

The measuring device: At-constant-pressure thickness measuring device TYPE PF-11 (manufactured by Rafurokku Co.)

2. Pressure observed when the sample was compressed by 50 %

A sample which had been cut into 10 mm x 10 mm size was placed on a pressure receiving plate and compressed at the compression rate of 0.5 mm/sec. The load was recorded when the thickness of the sample shrank to 50 % of the original thickness. The measured load was divided by the area of the sample, whereby the pressure at the time of 50 % compression was obtained.

3. Shielding property

The shielding property was measured according to the KEC

method, by using a sample of 120 mm x 120 mm size.

Specifically, the sample was placed between the antenna for transmission and the antenna for reception in a shielded box, and the strength of the received electromagnetic wave was measured. The damping rate (dB) was obtained from the ratio of the strength value of the received electromagnetic wave with respect to the strength value of the received electromagnetic wave when the sample was not present.

4. Metal separation

A sample of 50 mm x 50 mm size was placed on a white cloth. A roller of 500 g weight was placed on the sample. The roller was reciprocally operated on the sample 250 times, and then the condition of metal layer separation (peeling off) was visually evaluated.

○: Separation of metal was hardly observed.

△: Separation of metal was slightly observed.

×: Significant separation of metal was observed.

5. Cutting debris

The generation of cutting debris at the time of cutting the sample with a pair of scissors was visually observed.

◎: Cutting debris was hardly generated.

○: Cutting debris was slightly generated.

△: Cutting debris was moderately generated.

×: Cutting debris was significantly generated.

Example 1

A double raschel three dimensionally knitted structure

was produced by using the structure pattern as shown in Fig. 4 and a double raschel knitting device having 22 gauge. Polyester fiber of 33 dtex/12f was used as the ground structure. Monofilament made of polyester fiber of 22 dtex was used as the connection thread. A blank product of 24 course/inch and 22 well/inch was obtained.

Next, the obtained blank product was scoured and dried, whereby excess oil contents and impurities were removed. Thereafter, the blank product was immersed, for two minutes, in an aqueous solution at the temperature of 40 °C which contained 0.3 g/L of palladium chloride, 30 g/L of tin (I) chloride, and 300 ml/L of 36 % hydrochloric acid. The blank product was then washed with water. Thereafter, the blank product was immersed, for five minutes, in borofluoric acid whose acid concentration was 0.1 N at the temperature of 30 °C. The blank product was then washed with water. Next, the blank product was immersed, for five minutes, in an electroless copper plating solution at the temperature of 30 °C which contained 7.5 g/L of copper sulfate, 30 ml/L of 37 % formalin, and 85 g/L of Rochelle salt. The blank product was then washed with water. Thereafter, the blank product was immersed, for ten minutes and at the electric current density of 5A/dm², in an electrolytic nickel plating solution of pH 3.7 at the temperature of 35 °C which contained 300 g/L of nickel sulfamate, 30 g/L of boric acid, 15 g/L of nickel chloride, whereby nickel was plated on the product. The blank

product was then washed with water. The obtained metal-coated, three dimensionally knitted structure was immersed in the acrylic resin emulsion ("Primal TR-934", manufactured by NIPPON ACRYL KAGAKUSHA) for 30 seconds, so that excess resin was removed. The product was then dried, whereby an electromagnetic wave shielding material whose conductive metal layer was coated with the acrylic resin was obtained. The obtained electromagnetic wave shielding material exhibited little variation in thickness thereof, performances which were as excellent as those of the gasket employing the conventional foam, and significantly reduced level of metal separation and cutting debris generation. The observed performances are summarized in Table 1.

Example 2

A double raschel three dimensionally knitted structure was produced by using the same structure pattern as example 1 and a double raschel knitting device having 22 gauge. Polyester fiber of 33 dtex/12f was used at L1 and L6 of the ground structure. Polyester-based heat-fusing composite thread of 33 dtex/12f (the ratio of the core thereof made of regular polyester with respect to the sheath thereof made of low-melting point polyester being 1:1) was used at L2 and L5 of the ground structure. Monofilament made of polyester fiber of 22 dtex was used as the connection thread. A blank product of 24 course/inch and 22 well/inch was thus obtained. The weight percentage of the heat-

fusing thread used in the product was 65.4 %.

Next, the obtained blank product was scoured and dried, whereby excess oil contents and impurities were removed. Thereafter, the blank product was immersed, for two minutes, in an aqueous solution at the temperature of 40 °C which contained 0.3 g/L of palladium chloride, 30 g/L of tin (I) chloride, and 300 ml/L of 36 % hydrochloric acid. The blank product was then washed with water. Thereafter, the blank product was immersed, for five minutes, in borofluoric acid whose acid concentration was 0.1 N at the temperature of 30 °C. The blank product was then washed with water. Next, the blank product was immersed, for five minutes, in an electroless copper plating solution at the temperature of 30 °C which contained 7.5 g/L of copper sulfate, 30 ml/L of 37 % formalin, and 85 g/L of Rochelle salt. The blank product was then washed with water. Thereafter, the blank product was immersed, for ten minutes and at the electric current density of 5A/dm², in an electrolytic nickel plating solution of pH 3.7 at the temperature of 35 °C which contained 300 g/L of nickel sulfamate, 30 g/L of boric acid, 15 g/L of nickel chloride, whereby nickel was plated on the product. The blank product was then washed with water. An electromagnetic wave shielding material was obtained. The observed performances are summarized in Table 1.

Example 3

A double raschel three dimensionally knitted structure was produced by using the pattern structure as shown in Fig. 5 and a double raschel knitting device having 22 gauge. Polyester fiber of 33 dtex/12f was used at L1 and L6 of the ground structure. Polyester-based heat-fusing composite thread of 33 dtex/12f (the ratio of the core thereof made of regular polyester with respect to the sheath thereof made of low-melting point polyester being 1:1) was used at L2 and L5 of the ground structure. Monofilament made of polyester fiber of 22 dtex was used as the connection thread. A blank product of 24 course/inch and 22 well/inch was thus obtained. The percentage of the heat-fusing thread used in the product was 65.4 %.

Next, the product was processed in a manner similar to that of example 2, whereby an electromagnetic wave shielding material was obtained. Cutting of the electromagnetic wave shielding material was carried out at the portion not having the connection thread. The observed performances are summarized in Table 1.

Comparative Example 1

An elastic foam block made of polyether-based polyurethane having cell density of being 45 cell/inch was sliced by 2 mm by a slicer. A piece of Spanbond unwoven cloth made of polyester long fiber (single thread fiber degree of 2.2 dtex) was heat-fused to one side of the slice, and a piece of polyester fiber Tenjiku-ami knitting

structure (56 dtex/24f, 65 course/45 well, thread density being 54 g/m², thickness being 0.47 mm) was heat-fused to the other side of the slice, whereby a composite sheet of the three-layered structure having 1.4 mm thickness was obtained. The obtained composite sheet was processed in a manner similar to that of example 2, whereby an electromagnetic wave shielding material was obtained. The observed performances are summarized in Table 1.

Comparative Example 2

Lipstop woven fabric (thread density thereof being 120 longitudinal thread/inch and 130 transverse thread/inch) made of nylon long fiber (44 dtex/10f) was processed in a manner similar to that of example 2, whereby a conductive woven fabric was obtained. The obtained conductive woven fabric was wound around polyether-based polyurethane (the cell density thereof being 45 cell/inch) with the ester-based hotmelt provided therebetween, whereby an electromagnetic wave shielding material was obtained. The observed performances are summarized in Table 1.

Table 1

	Thickness (mm)	50% Compression Stress	Shielding property (dB 1GHz)	Metal Separation	Cutting debris
Example 1	2.25	11.8	85.0	○	○
Example 2	2.20	10.8	109.1	○	○
Example 3	2.20	10.7	109.0	○	◎
Comparative Example 1	1.40	19.1	90.0	△	×
Comparative Example 2	2.00	27.5	82.8	△	△

The present invention provides an electromagnetic wave shielding material, which can be produced by a relative small number of production steps, suppresses separation of coating metal and reduces the amount of cutting debris generated at the time of cutting.